

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

5

LISTING OF CLAIMS

1. (Canceled)

2. (Original) A neutral black ink for ink-jet printing, comprising:

10 an ink vehicle; carbon black, cyan pigment and violet pigment; wherein the absorbance ratio of carbon black: cyan pigment: violet pigment for black ink is 0.18:0.05:0.08 with values being measured at 1/5K dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black and each ratio value ranging +/- 25%;

15 and wherein the carbon black, cyan pigment and violet pigment are associated with a polymer or polymers which render the carbon black, cyan pigment and violet pigment dispersible in aqueous solution.

20 3. (Original) The neutral black ink of claim 2 wherein the wavelength of the peak maxima for the cyan of the neutral black ink is 610 to 620 nm.

4. (Original) The neutral black ink of claim 2 wherein the wavelength of the peak maxima for the violet of the neutral black ink is 530 to 540 nm.

25 5. (Original) The neutral black ink of claim 2, wherein the polymer or polymers comprise acrylates.

30 6. (Original) The neutral black ink of claim 2, wherein the neutral black ink is printed together with a neutral medium gray ink, the neutral medium gray ink comprising:

an ink vehicle; carbon black, cyan pigment and violet pigment; wherein the absorbance ratio of carbon black: cyan pigment: violet pigment for neutral medium gray ink is 0.04:0.01:0.02 with values being measured at 1/5K dilu-

tion, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black and each ratio value ranging +/- 25%.

5 7. (Original) The neutral black ink of claim 6 wherein the wavelength of the peak maxima for the cyan of the neutral medium gray ink is 610 to 620 nm.

8. (Original) The neutral black ink of claim 6 wherein the wavelength of the peak maxima for the violet of the neutral medium gray ink is 530 to 540 nm.

10

9. (Original) The neutral black ink of claim 2, wherein the neutral black ink is printed together with a neutral dark gray ink and a neutral light gray ink, the neutral dark gray ink comprising:

15 an ink vehicle; carbon black, cyan pigment and violet pigment; wherein the absorbance ratio of carbon black: cyan pigment: violet pigment for neutral dark gray ink is 0.06:0.02:0.03 with values being measured at 1/5K dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black and each ratio value ranging +/- 25% and the neutral light gray ink comprising:

20 an ink vehicle; carbon black, cyan pigment and violet pigment; wherein the absorbance ratio of carbon black: cyan pigment: violet pigment for neutral light gray ink is 0.02:0.01:0.01 with values being measured at 1/5K dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black and each ratio value ranging +/- 25%.

25 10. (Original) The neutral black ink of claim 9 wherein the wavelength of the peak maxima for the cyan of the neutral dark gray ink is 610 to 620 nm.

11. (Original) The neutral black ink of claim 9 wherein the wavelength of the peak maxima for the violet of the neutral dark gray ink is 530 to 540 nm.

30

12. (Original) The neutral black ink of claim 9 wherein the wavelength of the peak maxima for the cyan of the neutral light gray ink is 610 to 620 nm.

13. (Original) The neutral black ink of claim 9 wherein the wavelength of the peak maxima for the violet of the neutral light gray ink is 530 to 540 nm.

14. (Previously presented) The neutral black ink of claim 2, wherein the violet
5 pigment is selected from the group consisting of PV19, PV42, PV23, PV3,
PV19, PV32, PV36, and PV38.

15. (Original) The neutral black ink of claim 2, wherein the violet pigment has
a quinacridone or dioxazine based structure.

10

16. (Original) The neutral black ink of claim 2,
wherein the carbon black in the neutral black ink is from 1.568 to 2.613 weight
percent; the cyan pigment is from 0.317 to 0.529 weight percent and com-
prises PB15:4 cyan pigment; and the violet pigment is from 0.438 to 0.731
15 weight percent and comprises violet pigment.

17. (Original) The neutral black ink of claim 6, wherein the carbon black in the
neutral medium gray ink is from 0.314 to 0.523 weight percent carbon black;
the cyan pigment in the neutral medium gray ink is from 0.068 to 0.113 weight
20 percent and comprises PB15:4 cyan pigment; and the violet pigment in the
neutral medium gray ink is from 0.101 to 0.169 weight percent and com-
prises PV23 violet pigment.

18. (Original) The neutral black ink of claim 9, wherein the carbon black in the
25 neutral dark gray ink is from 0.517 to 0.862 weight percent carbon black; the
cyan pigment in the neutral dark gray ink is from 0.105 to 0.174 weight per-
cent and comprises PB15:4 cyan pigment; and the violet pigment in the
neutral dark gray ink is from 0.145 to 0.241 weight percent and comprises vio-
let pigment; and wherein the carbon black in the neutral light gray ink is from
30 0.172 to 0.287 weight percent carbon black; the cyan pigment in the neutral
light gray ink is from 0.035 to 0.058 weight percent and comprise cyan pig-
ment; and the violet pigment in the neutral light gray ink is from 0.048 to 0.080
weight percent and comprises PV23 violet pigment.

19. (Canceled)

20. (Original) An ink set for ink-jet printing, comprising an ink set of a neutral
5 black ink and at least one ink selected from the group consisting of neutral
medium gray ink, neutral dark gray ink, neutral light gray ink, cyan ink, ma-
genta ink, yellow ink, light cyan ink, light magenta ink, red ink, green ink, blue
ink, violet ink and orange ink;
wherein the absorbance ratio of carbon black: cyan pigment: violet pigment
10 for neutral black ink is 0.18:0.05:0.08 with values being measured at 1/5K di-
lution, at the peak maxima between 400nm and 700nm wavelength for cyan
and violet and at 500nm for carbon black and each ratio value ranging +/-
25%;
and wherein the carbon black, cyan pigment and violet pigment are associ-
15 ated with a polymer or polymers which render the carbon black, cyan pigment
and violet pigment dispersible in aqueous solution.

21. (Original) The ink set of claim 20 wherein the wavelength of the peak
maxima for the cyan of the neutral black ink is 610 to 620 nm.

20

22. (Original) The ink set of claim 20 wherein the wavelength of the peak
maxima for the violet of the neutral black ink is 530 to 540 nm.

23. (Original) The ink set of claim 20, wherein the polymer or polymers com-
25 prise acrylates.

24. (Original) The ink set of claim 20, wherein when the ink-set comprises
neutral medium gray ink, the absorbance ratio of carbon black: cyan pigment:
violet pigment for the neutral medium gray ink is 0.04:0.01:0.02 with values
30 being measured at 1/5K dilution, at the peak maxima between 400nm and
700nm wavelength for cyan and violet and at 500nm for carbon black and
each ratio value ranging +/- 25%.

25. (Original) The ink set of claim 24 wherein the wavelength of the peak maxima for the cyan of the neutral medium gray ink is 610 to 620 nm.

26. (Original) The ink set of claim 24 wherein the wavelength of the peak
5 maxima for the violet of the neutral medium gray ink is 530 to 540 nm.

27. (Original) The ink set of claim 20, wherein when the ink-set comprises neutral dark gray ink and neutral light gray ink, the absorbance ratio of carbon black: cyan pigment: violet pigment for the neutral dark gray ink is
10 0.06:0.02:0.03 with values being measured at 1/5K dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black and each ratio value ranging +/- 25 %;
and the absorbance ratio of carbon black: cyan pigment: violet pigment for the neutral light gray ink is 0.02:0.01:0.01 with values being measured at 1/5K
15 dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black and each ratio value ranging +/- 25%.

28. (Original) The ink set of claim 27 wherein the wavelength of the peak
20 maxima for the cyan of the neutral dark gray ink is 610 to 620 nm.

29. (Original) The ink set of claim 27 wherein the wavelength of the peak maxima for the violet of the neutral dark gray ink is 530 to 540 nm.

25 30. (Original) The ink set of claim 27 wherein the wavelength of the peak maxima for the cyan of the neutral light gray ink is 610 to 620 nm.

31. (Original) The ink set of claim 27 wherein the wavelength of the peak maxima for the violet of the neutral light gray ink is 530 to 540 nm.

30

32. (Original) The ink set of claim 20, wherein the ink set is a three-ink ink set comprising neutral black ink, neutral dark gray ink, and neutral light gray ink.

33. (Original) The ink set of claim 20, wherein the ink set is a six-ink ink set comprising neutral black ink, neutral gray ink for use with neutral light gray ink, neutral light gray ink, cyan ink, magenta ink, and yellow ink.

5 34. (Original) The ink set of claim 20, wherein the ink set is an eight-ink ink set comprising neutral black ink, neutral gray ink for use with neutral light gray ink, neutral light gray ink, cyan ink, magenta ink, yellow ink, light cyan ink and light magenta ink.

10 35. (Original) The ink set of claim 20, wherein the ink set is a twelve-ink ink set comprising neutral black ink, neutral medium gray ink, cyan ink, magenta ink, yellow ink, light cyan ink, light magenta ink, red ink, green ink, blue ink, violet ink, and orange ink.

15 36. (Original) The ink set of claim 20, wherein the violet pigment is selected from the group consisting of PV19, PV42, PV23, PV3, PV19, ~~PV23~~, PV32, PV36, and PV38.

20 37. (Original) The ink set of claim 20, wherein the violet pigment has a quina-
cridone or dioxazine based structure.

38. (Original) The ink set of claim 20, wherein the carbon black in the neutral black ink is from 1.568 to 2.613 weight percent; the cyan pigment in the neutral black ink is from 0.317 to 0.529 weight percent and comprises
25 PB15:4 cyan pigment; and the violet pigment in the neutral black ink is from 0.438 to 0.731 weight percent and comprises PV23 violet pigment.

39. (Original) The ink set of claim 24, wherein the carbon black in the neutral medium gray ink is from 0.314 to 0.523 weight percent carbon black; the cyan
30 pigment is from 0.068 to 0.113 weight percent and comprises PB15:4 cyan pigment; and the violet ink comprises from 0.101 to 0.169 weight percent and comprises PV23 violet pigment.

40. (Original) The ink set of claim 27, wherein the carbon black in the neutral dark gray ink is from 0.517 to 0.862 weight percent; the cyan pigment in the neutral dark gray ink is from 0.105 to 0.174 weight percent and comprises PB15:4 cyan pigment; and the violet pigment in the neutral dark gray ink is
5 from 0.145 to 0.241 weight percent and comprises PV23 violet pigment; and wherein the carbon black in the neutral light gray ink is from 0.172 to 0.287 weight percent; the cyan pigment in the neutral light gray ink is from 0.035 to 0.058 weight percent and comprises PB15:4 cyan pigment; and the violet pigment in the neutral light gray ink is from 0.048 to 0.080 weight per-
10 cent and comprises PV23 violet pigment.

41. (Canceled)

42. (Original) A method of printing gray, black and neutral areas with de-
15 creased browning and metamerism in ink-jet printing comprising:
printing on a medium with an ink set of neutral black and at least one ink selected from the group consisting of neutral medium gray ink, neutral dark gray ink, neutral light gray ink, cyan ink, magenta ink, yellow ink, light cyan ink, light magenta ink, red ink, green ink, blue ink, violet ink and orange
20 ink;
wherein the absorbance ratio of carbon black: cyan pigment: violet pigment for the neutral black ink is 0.18:0.05:0.08 with values being measured at 1/5K dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black and each ratio value ranging +/-
25 25%;
and wherein the carbon black, cyan pigment and violet pigment are associated with a polymer or polymers which render the carbon black, cyan pigment and violet pigment dispersible in aqueous solution.

30 43. (Original) The method of claim 42 wherein the wavelength of the peak maxima for the cyan of the neutral black ink is 610 to 620 nm.

44. (Original) The method of claim 42 wherein the wavelength of the peak maxima for the violet of the neutral black ink is 530 to 540 nm.

45. (Original) The method of claim 42, wherein the polymer or polymers are
5 acrylates.

46. (Original) The method of claim 42, wherein when the ink-set comprises neutral medium gray ink, the absorbance ratio of carbon black: cyan pigment: violet pigment for the neutral medium gray ink is 0.04:0.01:0.02 with values
10 being measured at 1/5K dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at 500nm for carbon black wavelength and each ratio value ranging +/-25 %.

47. (Original) The method of claim 46 wherein the wavelength of the peak
15 maxima for the cyan of the neutral medium gray ink is 610 to 620 nm.

48. (Original) The method of claim 46 wherein the wavelength of the peak maxima for the violet of the neutral medium gray ink is 530 to 540 nm.

20 49. (Original) The method of claim 42, wherein when the ink-set comprises neutral dark gray ink and neutral light gray ink, the absorbance ratio of carbon black: cyan pigment: violet pigment for the neutral dark gray ink is 0.06:0.02:0.03 with values being measured at 1/5K dilution, at the peak maxima between 400nm and 700nm wavelength for cyan and violet and at
25 500nm for carbon black and each ratio value ranging +/- 25%;
and the absorbance ratio of carbon black: cyan pigment: violet pigment for the neutral light gray ink is 0.02:0.01:0.01 with values being measured at 1/5K dilution, 400-700 wavelength and each ratio value ranging +/- 25%.

30 50. (Original) The method of claim 49 wherein the wavelength of the peak maxima for the cyan of the neutral dark gray ink is 610 to 620 nm.

51. (Original) The method of claim 49 wherein the wavelength of the peak maxima for the violet of the neutral dark gray ink is 530 to 540 nm.

52. (Original) The method of claim 49 wherein the wavelength of the peak
5 maxima for the cyan of the neutral light gray ink is 610 to 620 nm.

53. (Original) The method of claim 49 wherein the wavelength of the peak maxima for the violet of the neutral light gray ink is 530 to 540 nm.

54. (Original) The method of claim 42, wherein the ink set is a three-ink ink set
10 comprising neutral black ink, neutral dark gray ink, and neutral light gray ink.

55. (Original) The method of claim 42, wherein the ink set is a six-ink ink set
15 comprising neutral black ink, neutral dark gray ink, neutral light gray ink, cyan ink, magenta ink, and yellow ink.

56. (Original) The method of claim 42, wherein the ink set is an eight-ink ink
set comprising neutral black ink, neutral dark gray ink, neutral light gray ink,
cyan ink, magenta ink, yellow ink, light cyan ink and light magenta ink.

20

57. (Original) The method of claim 42, wherein the ink set is a twelve-ink ink
set comprising neutral black ink, neutral medium gray ink, cyan ink, magenta
ink, yellow ink, light cyan ink, light magenta ink, red ink, green ink, blue ink,
violet ink, and orange ink.

58. (Previously presented) The method of claim 42, wherein the violet pigment
25 is selected from the group consisting of PV19, PV42, PV23, PV3, PV19,
PV32, PV36, and PV38.

59. (Original) The method of claim 42, wherein the violet has a quinacridone
30 or dioxazine based structure.

60. (Original) The method of claim 42, wherein the carbon black in the neutral
black ink is from 1.568 to 2.613 weight percent; the cyan pigment in the neu-

tral black ink is from 0.317 to 0.529 weight percent and comprises PB15:4 cyan pigment; and violet pigment in the neutral black ink is from 0.438 to 0.731 weight percent and comprises PV23 violet pigment.

- 5 61. (Original) The method of claim 46, wherein the carbon black in the neutral medium gray ink is from 0.314 to 0.523 weight percent; the cyan pigment is from 0.068 to 0.113 weight percent and comprises PB15:4 cyan pigment; and the violet pigment is from 0.101 to 0.169 weight percent and comprises PV23 violet pigment.

10

62. (Original) The method of claim 49, wherein the carbon black in the neutral dark gray ink is from 0.517 to 0.862 weight percent; the cyan pigment in the neutral dark gray ink is from 0.105 to 0.174 weight percent and comprises PB15:4 cyan pigment; and the violet pigment in the neutral dark gray ink is from 0.145 to 0.241 weight percent violet pigment; and wherein the carbon black in the neutral light gray ink is from 0.172 to 0.287 weight percent; the cyan pigment in the neutral light gray ink is from 0.035 to 0.058 weight percent and comprises PB15:4 cyan pigment; and the violet pigment in the neutral light gray ink is from 0.048 to 0.080 weight percent and comprises PV23 violet pigment.
- 15
- 20